

PATENT ABSTRACTS OF JAPAN

A193

(11)Publication number : 09-087096

(43)Date of publication of application : 31.03.1997

(51)Int.Cl.

C30B 29/34
C01B 33/44
C08J 5/10
C08K 3/00

(21)Application number : 07-248167

(71)Applicant : NATL INST FOR RES IN INORG
MATER
SHOWA DENKO KK

(22)Date of filing : 26.09.1995

(72)Inventor : NAKAZAWA HIROMOTO
YAMADA HIROHISA
TAMURA TAKASHI
HOSOKAWA TERUO
INOUE HIROFUMI
MOGI YOSHIHIRO

(54) LIPOPHILIC INORGANIC FILLER AND COMPOSITE RESIN COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a lipophilic inorg. filler well swollen with a small amt. of org. cations and improving the heat resistance and rigidity of a composite resin compsn. having a high aspect ratio.

SOLUTION: Org. cations are intercalated into a swellable silicate represented by the formula $[Aa(XbYc)(Si_4-dAl_d)O_{12}(OH_eF_{2-e})]$ and having $\geq 2\mu m$ average grain diameter of single crystal grains, $70-250\text{\AA}$ /charge charge density and a smectite structure to obtain the objective lipophilic inorg. filler. In the formula, $0.2 \leq a \leq 0.7$, $0 \leq b \leq 3$, $0 \leq c \leq 2$, $0 \leq d \leq 4$, $0 \leq e \leq 2$, A is at least one cation selected from among alkali metal ions and alkaline earth metal ions, X and Y are cations entering into each octahedron in the smectite structure, X is at least one among Mg, Fe, Mn, Ni, Zn and Li, and Y is at least one among Al, Fe, Mn and Cr.

LEGAL STATUS

[Date of request for examination]

10.04.2002